



Price Supply, Inc.

1-800-444-2597

200 lb Grab Tensile Woven Stabilization Geotextile Fabric

This engineered geotextile is stabilized to resist degradation due to ultraviolet exposure. It is resistant to commonly encountered soil chemicals, mildew and insects, and is non-biodegradable.

Property	Test Method	Minimum Average Roll Value (English)	Minimum Average Roll Value (Metric)
Grab Tensile	ASTM-D-4632	200 lbs	.9 kN
Grab Elongation	ASTM-D-4632	15%	15%
Mullen Burst	ASTM-D-3786	400 psi	2758 kpa
CBR Puncture Resistance	ASTM-D-6241	700 lbs	3.12 kN
Trapezoidal Tear	ASTM-D-4533	75 lbs	.334 kN
UV Resistance	ASTM-D-4355	70 % at 700 hr	70 % at 700 hr
Permittivity	ASTM-D-4491	0.05 sec ⁻¹	0.05 sec ⁻¹
AOS	ASTM-D-4751	40 Sieve	0.425 mm
Flow Rate	ASTM-D-4491	5 gal/min/sq.ft.	203 l/min/m ²